

**Test Report No.: 68.431.19.04475.01**

**Dated: 2019-09-20**



**Applicant** : Spector & Co

**Address** : /

**Sample Description** : PERFECT BOUND LEATHER JOURNAL

**Product Type / End Use** : JOURNAL

**PO / Order No.** : N/A

**Item No.** : ST601

**Style No.** : GIUSEPPE

**Supplier** : USG040

**Country of Origin** : China

**Exported to** : Canada & U.S.A.

**Test Sample Receipt Date, Location** : 2019-09-06, Shenzhen

**Test Period, Location** : From 2019-09-09 to 2019-09-19, Shenzhen

**Test Result(s)** : Refer to Section 3



**Purpose Of Examination / Conclusion:**

No.	Test Item(s)	Conclusion
1.	US California Proposition 65 - Total Cadmium Content Test - Substrate Materials	Pass*
2.	US California Proposition 65 - Total Lead Content Test - Substrate Materials	Pass*
3.	Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test	Pass
4.	Phthalates Content	Pass*
5.	US California Proposition 65 - Phthalates Content	Pass*
6.	U.S. CFR Title 16 Part 1307 - Phthalates Content	Pass

Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) "\*" denotes the conclusion was drawn according to the client's specification.
- (4) The test item and samples were specified by the client
- (5) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expanded uncertainty for "pass", "Fail" and "Inconclusive" is 95%.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 TÜV SÜD Group

Prepared by:

Reviewed by:



<Cara Xiang>  
 <Senior Project Coordinator>


<Ken Chen>  
 <Project Manager>


Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

1. Description of the Test Sample:

<b>Sample Description</b>	PERFECT BOUND LEATHER JOURNAL
---------------------------	-------------------------------

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Black soft plastic w/ black paper (Cover & back)	
T2	002	Brown soft plastic w/ black paper (Cover & back)	
T3	003	Navy blue soft plastic w/ black paper (Cover & back)	
T4	004	Black soft plastic (Elastic band)	





**3. Test Result**

**3.1 US California Proposition 65 - Total Cadmium Content Test - Substrate Materials**

Test method: Acid digestion/Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test item	Results [mg/kg]		Client's Specification [mg/kg]
	Sample 001+002+003	Sample 004	
Cadmium	N.D.	N.D.	<75
<b>Conclusion</b>	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

**3.2 US California Proposition 65 - Total Lead Content Test - Substrate Materials**

Test method: Acid digestion or Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]		Client's Specification [mg/kg]
	Sample 001+002+003	Sample 004	
Lead	N.D.	N.D.	<100
<b>Conclusion</b>	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg



**3.3 Total Lead Content Test**

Consumer Products Containing Lead Regulations SOR/2018-83  
 Acid digestion / Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).


[Reporting Limit: 10.0mg/kg]

Analyte	Result [mg/kg]	
	Sample 001+002+003	Sample 004
Lead	N.D.	N.D.
Limit	<90	
Conclusion	Pass	Pass

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg



### 3.4 Phthalates Content

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]		Client's Specification [%]
		Sample 001+002+003	Sample 004	
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	<0.1
Di-n-pentylphthalat (DNPP)	131-18-0	N.D.	N.D.	<0.1
<b>Conclusion</b>		Pass	Pass	-

Note 1. “%” denotes percentage by weight

2. “<” denotes less than

3. “N.D.” denotes Not Detected with Detection Limit 0.005%



**3.5 US California Proposition 65 - Phthalates Content**

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]		Client's Specification [%]
		Sample 001+002+003	Sample 004	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
<b>Conclusion</b>		Pass	Pass	-

- Note 1. “%” denotes percentage by weight  
 2. “<” denotes less than  
 3. “N.D.” denotes Not Detected with Detection Limit 0.005%



**3.6 U.S. CFR Title 16 Part 1307 - Phthalates Content**

CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates  
 [Reporting Limit = 0.005%]

Phthalates	CAS No.	Results [%]		Limit [%]
		Sample 001+002+003	Sample 004	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	<0.1
<b>Conclusion</b>		Pass	Pass	-

- Note 1. “%” denotes percentage by weight  
 2. “<” denotes less than  
 3. “N.D.” denotes Not Detected with Detection Limit 0.005%

-- END OF TEST REPORT--