

Test Report No.: 68.431.19.04682.01

Dated: 2019-09-30



Applicant : SPECTOR

Address : /

Sample Description : Vinyl Wine carrier Case

Item No. : SH101

Style No. : Fabrizio

Supplier : USS079

Country of Origin : China

Exported to : Canada & U.S.A.

Test Sample Receipt Date, Location : 2019-09-23, Shenzhen

Test Period, Location : From 2019-09-23 to 2019-09-29, Shenzhen

Test Result(s) : Refer to Section 3

Purpose Of Examination / Conclusion:

No.	Test Item(s)	Conclusion
1.	US California Proposition 65 - Total Cadmium Content Test - Substrate Materials	Pass*
2.	US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials	Pass*
3.	US California Proposition 65 - Total Lead Content Test - Substrate Materials	Pass*
4.	US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials	Pass*
5.	Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test	Pass
6.	Canadian Surface Coating Materials Regulations SOR/2016-193 – Total Lead Content Test	Pass
7.	Phthalates Content	Pass*
8.	US California Proposition 65 - Phthalates Content	Pass*
9.	U.S. CFR Title 16 Part 1307 - Phthalates Content	Pass
10.	Tungsten Content Test	Report as is
11.	Canadian Surface Coating Materials Regulations SOR/2016-193 - Total Mercury Content Test	Pass

Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) "*" denotes the conclusion was drawn according to the client's specification.
- (4) The test item and samples were specified by the client
- (5) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expanded uncertainty for "pass", "Fail" and "Inconclusive" is 95%.

Test Report No.: 68.431.19.04682.01

Dated: 2019-09-30



TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group

Prepared by:


Reviewed by:



<Cara Xiang>
<Senior Project Coordinator>

<Ken Chen>
<Project Manager>

Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.



Laboratory:
TÜV SÜD Certification and
Testing (China) Co., Ltd.
Shenzhen Branch

Phone : +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web : <http://www.tuv-sud.cn>



Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park,
Nantou Checkpoint Road 2, 518052, P. R. China

1. Description of the Test Sample:

Sample Description	Vinyl Wine carrier Case
--------------------	-------------------------

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Brown PU w/ matt brown fabric backing (Case)	
T2	002	Black coating (Zipper head & puller)	
T3	003	Silvery metal (Zipper head)	
T4	004	Silvery metal (Zipper puller)	
T5	005	Black plastic (Zipper teeth)	
T6	006	Silvery metal (Rivet)	
T7	007	Silvery metal (Square loop of handle)	
T8	008	Black hook & loop fastener (Velcro)	

T. No.	Sample No.	Colour and Description	Photograph
T9	009	White foam (Inner case)	
T10	010	Black PU w/ matt black fabric backing (Case)	

3. Test Result

3.1 US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test method: Acid digestion/Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 001+010	Sample 003	Sample 004	
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Test item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 005	Sample 006	Sample 007	
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Test item	Results [mg/kg]		Client's Specification [mg/kg]
	Sample 008	Sample 009	
Cadmium	N.D.	N.D.	<75
Conclusion	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg


3.2 US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials

Test method: Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]	Client's Specification [mg/kg]
	Sample 002	
Cadmium	N.D.	<75
Conclusion	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg



3.3 US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test method: Acid digestion or Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 001+010	Sample 003	Sample 004	
Lead	N.D.	31.6	N.D.	<100
Conclusion	Pass	Pass	Pass	-

Test Item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 005	Sample 006	Sample 007	
Lead	N.D.	N.D.	N.D.	<100
Conclusion	Pass	Pass	Pass	-

Test Item	Results [mg/kg]		Client's Specification [mg/kg]
	Sample 008	Sample 009	
Lead	N.D.	N.D.	<100
Conclusion	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg


3.4 US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials

Test method: Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]	Client's Specification [mg/kg]
	Sample 002	
Lead	N.D.	<90
Conclusion	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg



3.5 Total Lead Content Test

Consumer Products Containing Lead Regulations SOR/2018-83

Acid digestion / Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

[Reporting Limit: 10.0mg/kg]

Analyte	Result [mg/kg]		
	Sample 001+010	Sample 002	Sample 003
Lead	N.D.	N.D.	31.6
Limit	<90		
Conclusion	Pass	Pass	Pass

Analyte	Result [mg/kg]		
	Sample 004	Sample 005	Sample 006
Lead	N.D.	N.D.	N.D.
Limit	<90		
Conclusion	Pass	Pass	Pass

Analyte	Result [mg/kg]		
	Sample 007	Sample 008	Sample 009
Lead	N.D.	N.D.	N.D.
Limit	<90		
Conclusion	Pass	Pass	Pass

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg



3.6 Total Lead Content Test

Surface Coating Materials Regulations SOR/2016-193


Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Analyte	Result [mg/kg]
	Sample 002
Lead	N.D.
Limit	<90
Conclusion	Pass

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg



3.7 Phthalates Content

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]			Client's Specification [%]
		Sample 001+010	Sample 002	Sample 005	
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-n-pentylphthalat (DNPP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.7 Phthalates Content

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]		Client's Specification [%]
		Sample 008	Sample 009	
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	<0.1
Di-n-pentylphthalat (DNPP)	131-18-0	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.8 US California Proposition 65 - Phthalates Content

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]			Client's Specification [%]
		Sample 001+010	Sample 002	Sample 005	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Test Items	CAS No.	Results [%]		Client's Specification [%]
		Sample 008	Sample 009	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.9 U.S. CFR Title 16 Part 1307 - Phthalates Content

CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates

[Reporting Limit = 0.005%]

Phthalates	CAS No.	Results [%]			Limit [%]
		Sample 001+010	Sample 002	Sample 005	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.9 U.S. CFR Title 16 Part 1307 - Phthalates Content

CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates
[Reporting Limit = 0.005%]

Phthalates	CAS No.	Results [%]		Limit [%]
		Sample 008	Sample 009	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.10 Tungsten Content Test

Test method: EPA 3050B:1996, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]	Client's Specification [mg/kg]
	Sample 007	
Tungsten	N.D.	-
Conclusion	Report as is	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.11 Total Mercury Content Test

Surface Coating Materials Regulations SOR/2016-193

Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10mg/kg]

Test Item	Results [mg/kg]	Limit [mg/kg]
	Sample 002	
Mercury	N.D.	<10
Conclusion	Pass	-

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

-- END OF TEST REPORT--