

Applicant : Spector & Co
Address : /
Sample Description : LUGGAGE TAG
Product Type / End Use : TRAVEL
Item No. : G8028
Style No. : COLORPLAY
Supplier : USF019
Country of Origin : China
Exported to : Canada & U.S.A.
Test Sample Receipt Date, Location : 2019-11-01, 2019-12-24, Shenzhen
Test Period, Location : From 2019-11-01 to 2019-12-27, Shenzhen
Test Result(s) : Refer to Section 3

Purpose Of Examination / Conclusion:

No.	Test Item(s)	Conclusion
1.	US California Proposition 65 - Total Cadmium Content Test - Substrate Materials	Pass*
2.	US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials	Pass*
3.	US California Proposition 65 - Total Lead Content Test - Substrate Materials	Pass*
4.	US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials	Pass*
5.	Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test	Pass
6.	Canadian Surface Coating Materials Regulations SOR/2016-193 – Total Lead Content Test	Pass
7.	Phthalates Content (11P)	Pass*



No.	Test Item(s)	Conclusion
8.	US California Proposition 65 - Phthalates Content (6P)	Pass*
9.	U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)	Pass
10.	Tungsten Content Test	Report as is
11.	Canadian Surface Coating Materials Regulations SOR/2016-193 - Total Mercury Content Test	Pass

Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) "*" denotes the conclusion was drawn according to the client's specification.
- (4) The test item and samples were specified by the client
- (5) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expanded uncertainty for "pass", "Fail" and "Inconclusive" is 95%.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group

Prepared by:

Reviewed by:

Cara



Ken

<Cara Xiang>
<Senior Project Coordinator>


<Ken Chen>
<Project Manager>



Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

1. Description of the Test Sample:

Sample Description	LUGGAGE TAG
--------------------	-------------

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Orange coating (Rim of hanger)	
T2	002	Orange leather w/ grey layer (Luggage tag)	
T3	003	Khaki fabric w/ glue (Lining)	
T4	004	White non-woven (Inner luggage tag)	
T5	005	Matt orange PU w/ white net fabric backing (Rim of widow)	
T6	006	Clear PVC (Window)	
T7	007	Clear laminated black printed white paper (Name card)	

T. No.	Sample No.	Colour and Description	Photograph
T8	008	Silvery metal (Buckle)	
T9	009	Silvery metal (Pin of buckle)	
T10	010	Silvery metal (Rivet)	
T11	011	Black coating (Rim of hanger)	
T12	012	Black leather w/ grey layer (Luggage tag)	
T13	014	Red coating (Rim of hanger)	
T14	015	Red leather w/ grey layer (Luggage tag)	
T15	016	Red PU w/ white net fabric backing (Rim of widow)	
T16	017	Blue coating (Rim of hanger)	
T17	018	Blue leather w/ grey layer (Luggage tag)	
T18	020	Green coating (Rim of hanger)	
T19	021	Green leather w/ grey layer (Luggage tag)	
T20	022	Green PU w/ white net fabric backing (Rim of widow)	

3. Test Result

3.1 US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test method: Acid digestion/Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 002+012+015	Sample 003	Sample 004	
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Test item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 005	Sample 006	Sample 007	
Cadmium	64.6	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Test item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 008	Sample 009	Sample 010	
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Test item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 016	Sample 018+021	Sample 022	
Cadmium	64.2	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.2 US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials

Test method: Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 001	Sample 011	Sample 014	
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Test Item	Results [mg/kg]		Client's Specification [mg/kg]
	Sample 017	Sample 020	
Cadmium	N.D.	N.D.	<75
Conclusion	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.3 US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test method: Acid digestion or Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 002+012+015	Sample 003	Sample 004	
Lead	N.D.	N.D.	N.D.	<100
Conclusion	Pass	Pass	Pass	-

Test Item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 006	Sample 007	Sample 008	
Lead	N.D.	N.D.	20.1	<100
Conclusion	Pass	Pass	Pass	-

Test Item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 009	Sample 010	Sample 018+021	
Lead	24.1	30.0	N.D.	<100
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.4 US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials

Test method: Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]			Client's Specification [mg/kg]
	Sample 001	Sample 011	Sample 014	
Lead	N.D.	N.D.	N.D.	<90
Conclusion	Pass	Pass	Pass	-

Test Item	Results [mg/kg]		Client's Specification [mg/kg]
	Sample 017	Sample 020	
Lead	N.D.	N.D.	<90
Conclusion	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.5 Total Lead Content Test

Consumer Products Containing Lead Regulations SOR/2018-83

Acid digestion / Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

[Reporting Limit: 10.0mg/kg]

Analyte	Result [mg/kg]		
	Sample 001	Sample 002+012+015	Sample 003
Lead	N.D.	N.D.	N.D.
Limit	<90		
Conclusion	Pass	Pass	Pass

Analyte	Result [mg/kg]		
	Sample 004	Sample 006	Sample 007
Lead	N.D.	N.D.	N.D.
Limit	<90		
Conclusion	Pass	Pass	Pass

Analyte	Result [mg/kg]		
	Sample 008	Sample 009	Sample 010
Lead	20.1	24.1	30.0
Limit	<90		
Conclusion	Pass	Pass	Pass

Analyte	Result [mg/kg]		
	Sample 011	Sample 014	Sample 017
Lead	N.D.	N.D.	N.D.
Limit	<90		
Conclusion	Pass	Pass	Pass

Analyte	Result [mg/kg]	
	Sample 018+021	Sample 020
Lead	N.D.	N.D.
Limit	<90	
Conclusion	Pass	Pass

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.6 Total Lead Content Test

Surface Coating Materials Regulations SOR/2016-193

Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Analyte	Result [mg/kg]		
	Sample 001	Sample 011	Sample 014
Lead	N.D.	N.D.	N.D.
Limit	<90		
Conclusion	Pass	Pass	Pass

Analyte	Result [mg/kg]	
	Sample 017	Sample 020
Lead	N.D.	N.D.
Limit	<90	
Conclusion	Pass	Pass

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.7 Phthalates Content (11P)

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]			Client's Specification [%]
		Sample 001+011 +014	Sample 002+012 +015	Sample 003	
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	0.013	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-n-pentylphthalat (DNPP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.7 Phthalates Content (11P)

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]			Client's Specification [%]
		Sample 004	Sample 006*	Sample 007	
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	0.008	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-n-pentylphthalat (DNPP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

4. "*" denotes sample was received on 2019-12-24

3.7 Phthalates Content (11P)

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]		Client's Specification [%]
		Sample 017+020	Sample 018+021	
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	<0.1
Di-n-pentylphthalat (DNPP)	131-18-0	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.8 US California Proposition 65 - Phthalates Content (6P)

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]			Client's Specification [%]
		Sample 001+011 +014	Sample 002+012 +015	Sample 003	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	0.013	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Test Items	CAS No.	Results [%]			Client's Specification [%]
		Sample 004	Sample 006*	Sample 007	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	0.008	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

4. "*" denotes sample was received on 2019-12-24

3.8 US California Proposition 65 - Phthalates Content (6P)

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%]		Client's Specification [%]
		Sample 017+020	Sample 018+021	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.9 U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)

CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates
[Reporting Limit = 0.005%]

Phthalates	CAS No.	Results [%]			Limit [%]
		Sample 001+011 +014	Sample 002+012 +015	Sample 003	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	0.013	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

3.9 U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)

CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates
[Reporting Limit = 0.005%]

Phthalates	CAS No.	Results [%]			Limit [%]
		Sample 004	Sample 006*	Sample 007	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	0.008	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. “%” denotes percentage by weight

2. “<” denotes less than

3. “N.D.” denotes Not Detected with Detection Limit 0.005%

4. “*” denotes sample was received on 2019-12-24

3.9 U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)

CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates
[Reporting Limit = 0.005%]

Phthalates	CAS No.	Results [%]		Limit [%]
		Sample 017+020	Sample 018+021	
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	-

Note 1. “%” denotes percentage by weight

2. “<” denotes less than

3. “N.D.” denotes Not Detected with Detection Limit 0.005%

3.10 Tungsten Content Test

Test method: EPA 3050B:1996, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

Test Item	Results [mg/kg]	Client's Specification [mg/kg]
	Sample 008	
Tungsten	N.D.	-
Conclusion	Report as is	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.11 Total Mercury Content Test

Surface Coating Materials Regulations SOR/2016-193

Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10mg/kg]

Test Item	Results [mg/kg]			Limit [mg/kg]
	Sample 001	Sample 011	Sample 014	
Mercury	N.D.	N.D.	N.D.	<10
Conclusion	Pass	Pass	Pass	-

Test Item	Results [mg/kg]		Limit [mg/kg]
	Sample 017	Sample 020	
Mercury	N.D.	N.D.	<10
Conclusion	Pass	Pass	-

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

-- END OF TEST REPORT--