

Dated: 2019-11-25



Applicant : Spector & Co

Address : /

Sample Description : RAW MATERIAL

Product Type / End Use : BAGS

item No. : BG104, BG106, BG205, BG400, BG704

PO / Order No. : 7117800 & 7117900

Style No. : NOMAD MUST HAVES

Supplier : USB059

Country of Origin : China

Exported to : Canada & U.S.A.

Test Sample Receipt Date, Location : 2019-11-18, Shenzhen

Test Period, Location : From 2019-11-18 to 2019-11-22, Shenzhen

Test Result(s) : Refer to Section 3

Purpose Of Examination / Conclusion:

No.	Test Item(s)	Conclusion
1.	US California Proposition 65 - Total Cadmium Content Test - Substrate	Pass*
'.	Materials	rass
2.	US California Proposition 65 - Total Cadmium Content Test - Paint and	Pass*
Z .	Similar Surface-Coating Materials	rass
3.	US California Proposition 65 - Total Lead Content Test - Substrate	Pass*
ا ا	Materials	rass
4.	US California Proposition 65 - Total Lead Content Test - Paint and Similar	Pass*
4.	Surface-Coating Materials	Pass
5.	Canadian Consumer Products Containing Lead Regulations SOR/2018-	Pass
٥.	83 - Total Lead Content Test	F 455
6.	Canadian Surface Coating Materials Regulations SOR/2016-193 –	Pass
	Total Lead Content Test	F a 5 5

Laboratory:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Phone: +86 755 8828 6998 Fax: +86 755 8828 5299

E-mail: toys_hardline@tuv-sud.hk
Web : http://www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Building 12&13, Zhiheng Wisdomland Business Park,

Nantou Checkpoint Road 2, 518052, P. R. China

TI'N /®

Dated: 2019-11-25



No.	Test Item(s)	Conclusion
7.	Phthalates Content (11P)	Pass*
8.	US California Proposition 65 - Phthalates Content (6P)	Pass*
9.	U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates	Pass
9.	Content (8P)	F 433
10.	Tungsten Content Test	Report as is
11.	Canadian Surface Coating Materials Regulations SOR/2016-193 -	Pass
11.	Total Mercury Content Test	1 433


Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) "*" denotes the conclusion was drawn according to the client's specification.
- (4) The test item and samples were specified by the client
- (5) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expended uncertainty for "pass", "Fail" and "Inconclusive" is 95%.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch TÜV SÜD Group

Prepared by:

Reviewed by:





<Ken Chen>
<Project Manager>

<Cara Xiang>
<Senior Project Coordinator>

Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

Dated: 2019-11-25



1. Description of the Test Sample:

Sample Description	RAW MATERIAL

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Black PVC (Belt)	3 4 5 6 7 8 9 60 1 2 3 4 5 6 7 8 9 70 1 2 3 4 5 6 7 8 9 80 1 2
T2	002	Black / white coating (Sewn label)	# 10
Т3	003	Black soft plastic (Elastic band)	7 8 9 50 1 2 3 4 5 6 7 8 9 60 1 2 3 4 5 6 7 8 9 70 1

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: toys_hardline@tuv-sud.hk

Web: http://www.tuv-sud.cn



Dated: 2019-11-25



T. No.	Sample No.	Colour and Description	Photograph
T4	005	Silvery metal (Upper part of button)	
T5	006	Silvery metal (Cover of lower part of button)	
Т6	007	Silvery metal (Sunken of lower part of button)	
T7	800	Silvery metal (Cover of snap)	
Т8	009	Silvery metal (Frame of buckle)	
Т9	010	Silvery metal (Pin of buckle)	
T10	011	Silvery metal (Tubular of buckle)	
T11	012	Silvery metal (Pin of button)	
T12	013	Silvery metal (Pin of snap)	
T13	014	Black coating (Zipper head & puller)	
T14	015	Silvery metal (Small zipper head)	The state of the s
T15	016	Silvery metal (Small zipper puller)	
T16	017	Black plastic (Zipper teeth)	
T17	018	Silvery metal (Large zipper head)	
T18	019	Silvery metal (Large zipper puller)	

Dated: 2019-11-25



T. No.	Sample No.	Colour and Description	Photograph
T19	020	Silvery metal (Zipper teeth)	
T20	021	Silvery metal (Long zipper head)	
T21	022	Silvery metal (Long zipper puller)	
T22	024	Black plastic (Buckle)	
		SÜD	1234567896012345678970123456789801234567
T23	025	Silvery metal (Eyelet)	
T24	026	Silvery metal (Washer of eyelet)	50123456789601234567897012345
T25	027	Black plastic (Lobster hook)	
T26	028	Silvery metal (Lobster hook)	
T27	029	Silvery metal (Buckle)	Say S
T28	030	Silvery metal (Stick of buckle)	789501234567896012345678970123456789801

Laboratory:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Building 12&13, Zhiheng Wisdomland Business Park, Nantou Checkpoint Road 2, 518052, P. R. China Page 5 of 2



Dated: 2019-11-25



T. No.	Sample No.	Colour and Description	Photograph
T29	031	Matt black plastic (Adjuster, loop & lock)	9101234567895012345678960123456789701234
T30	032	Silvery metal (Frame of lobster hook)	
T31	033	Silvery metal (Arm of lobster hook)	
T32	034	Silvery metal (Axle of lobster hook)	
T33	035	Silvery metal (Movable part of lobster hook)	789501234567896012345678970123456
T34	036	Silvery metal (Loop)	78950123456789601234567897012345678
T35	037	Silvery metal (Square loop)	7 8 9 501 2 3 4 5 6 7 8 9 601 2 3 4 5 6 7 8 9 701 2 3 4 5 6

Laboratory:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Building 12&13, Zhiheng Wisdomland Business Park, Nantou Checkpoint Road 2, 518052, P. R. China Page 6 of 2



Dated: 2019-11-25



T. No.	Sample No.	Colour and Description	Photograph
T36	038	Silvery metal (Spring inner lock)	3 4 5 6 7 8 9 60 1 2 3 4 5 6 7 8 9 70 1 2 3 4 5 6 7 8 9 80
Т37	039	White foam (Sheet)	6789301234567896012345678970123456789301234567893012
T38	040	Deep grey fabric w/ black PVC backing (Sheet)	7234567899072345678990123456789701707070707070707070707070707070707070
Т39	041	Black fabric w/ black PVC backing (Sheet)	567693012345678900123456789701234567890012345618930

Laboratory:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Building 12&13, Zhiheng Wisdomland Business Park, Nantou Checkpoint Road 2, 518052, P. R. China Page 7 of



Dated: 2019-11-25



3. **Test Result**

3.1 US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test method: Acid digestion/Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	Results [mg/kg]			Client's
Test item	Sample 001+040+041	Sample 003	Sample 005	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

		Results [mg/kg]		
Test item	Sample 006	Sample 007	Sample 008	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

	Results [mg/kg]			Client's
Test item	Sample	Sample	Sample	Specification
	009	010	011	[mg/kg]
Cadmium	13.5	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

	Results [mg/kg]			Client's
Test item	Sample 012	Sample 013	Sample 015	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

		Client's		
Test item	Sample 016	Sample 017+024+027	Sample 018	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Phone: +86 755 8828 6998 Fax: +86 755 8828 5299 E-mail: toys_hardline@tuv-sud.hk

Web: http://www.tuv-sud.cn

Dated: 2019-11-25



3.1 US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test method: Acid digestion/Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	I	Client's		
Test item	Sample 019	Sample 020	Sample 021	Specification [mg/kg]
Cadmium	N.D.	N.D.	20.1	<75
Conclusion	Pass	Pass	Pass	-

Test item		Results [mg/kg]			Client's
		Sample 022	Sample 025	Sample 026	Specification [mg/kg]
Cadmium		N.D.	N.D.	N.D.	<75
Conclusion		Pass	Pass	Pass	-

		Results [mg/kg]		
Test item	Sample 028	Sample 029	Sample 030	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-
	301			

		Client's		
Test item	Sample 031	Sample 032	Sample 033	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

	i i	Client's		
Test item	Sample 034	Sample 035	Sample 036	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: toys_hardline@tuv-sud.hk

Web: http://www.tuv-sud.cn



Dated: 2019-11-25



3.1 US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test method: Acid digestion/Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	I	Client's		
Test item	Sample 037	Sample 038	Sample 039	Specification [mg/kg]
Cadmium	N.D.	N.D.	N.D.	<75
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.2 US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials

Test method: Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	Results	Client's		
Test Item	Sample 002	Sample 014	Specification [mg/kg]	
Cadmium	N.D.	N.D.	<75	
Conclusion	Pass	Pass	-	

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Shenzhen Branch

Dated: 2019-11-25



3.3 US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test method: Acid digestion or Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	F	Client's		
Test Item	Sample 001+040+041	Sample 003	Sample 005	Specification [mg/kg]
Lead	N.D.	N.D.	23.5	<100
Conclusion	Pass	Pass	Pass	-

		Results [mg/kg]		
Test Item	Sample	Sample	Sample	Specification
//	006	007	008	[mg/kg]
Lead	N.D.	N.D.	N.D.	<100
Conclusion	Pass	Pass	Pass	-

Test Item		Client's		
	Sample 009	Sample 010	Sample 011	Specification [mg/kg]
Lead	29.8	N.D.	N.D.	<100
Conclusion	Pass	Pass	Pass	-

		Client's		
Test Item	Sample	Sample	Sample	Specification
	012	013	015	[mg/kg]
Lead	N.D.	N.D.	25.6	<100
Conclusion	Pass	Pass	Pass	-

	Results [mg/kg]			Client's
Test Item	Sample 016	Specification [mg/kg]		
Lead	27.0	N.D.	31.6	<100
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: toys_hardline@tuv-sud.hk

Web: http://www.tuv-sud.cn

Dated: 2019-11-25



3.3 US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test method: Acid digestion or Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	Results [mg/kg]			Client's
Test Item	Sample 019	Sample 020	Sample 021	Specification [mg/kg]
Lead	27.3	12.7	38.2	<100
Conclusion	Pass	Pass	Pass	-

		Results [mg/kg]		
Test Item	Sam 022	•	Sample 026	Specification [mg/kg]
Lead	29.	4 N.D.	N.D.	<100
Conclusion	Pas	s Pass	Pass	-

		Results [mg/kg]		
Test Item	Sample 028	Sample 029	Sample 030	Specification [mg/kg]
Lead	N.D.	N.D.	N.D.	<100
Conclusion	Pass	Pass	Pass	-

	Results [mg/kg]			Client's
Test Item	Sample 031	Sample 032	Sample 033	Specification [mg/kg]
Lead	N.D.	14.8	13.0	<100
Conclusion	Pass	Pass	Pass	-

	Results [mg/kg]			Client's
Test Item	Sample 034	Sample 035	Sample 036	Specification [mg/kg]
Lead	N.D.	36.3	N.D.	<100
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

Dated: 2019-11-25



3.3 US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test method: Acid digestion or Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	Results [mg/kg]			Client's
Test Item	Sample 037	Sample 038	Sample 039	Specification [mg/kg]
Lead	N.D.	N.D.	N.D.	<100
Conclusion	Pass	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.4 US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials

Test method: Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	Results	Client's	
Test Item	Sample 002	Sample 014	Specification [mg/kg]
Lead	N.D.	N.D.	<90
Conclusion	Pass	Pass	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Nantou Checkpoint Road 2, 518052, P. R. China

Page 13 of 25

Dated: 2019-11-25



3.5 Total Lead Content Test

Consumer Products Containing Lead Regulations SOR/2018-83 Acid digestion / Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

[Reporting Limit: 10.0mg/kg]

	Result [mg/kg]			
Analyte	Sample	Sample	Sample	
	001+040+041	002	003	
Lead	N.D.	N.D.	N.D.	
Limit		<90		
Conclusion	Pass	Pass	Pass	

/	/	Result [mg/kg]			
Analyte	Sample	Sample	Sample		
	005	006	007		
Lead	23.5	N.D.	N.D.		
Limit		<90			
Conclusion	Pass	Pass	Pass		

		Result [mg/kg]				
Analyte	Sample 008	Sample 009	Sample 010			
Lead	N.D.	29.8	N.D.			
Limit		<90				
Conclusion	Pass	Pass	Pass			

	Result [mg/kg]				
Analyte	Sample	Sample	Sample		
	011	012	013		
Lead	N.D.	N.D.	N.D.		
Limit	<90				
Conclusion	Pass	Pass	Pass		

		Result [mg/kg]				
Analyte	Sample 014	-				
Lead	N.D.	25.6	27.0			
Limit		<90				
Conclusion	Pass	Pass	Pass			

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Laboratory: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: toys_hardline@tuv-sud.hk

Web: http://www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Building 12&13, Zhiheng Wisdomland Business Park,

Nantou Checkpoint Road 2, 518052, P. R. China

age 14 01 25



Dated: 2019-11-25



3.5 Total Lead Content Test

Consumer Products Containing Lead Regulations SOR/2018-83 Acid digestion / Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

[Reporting Limit: 10.0mg/kg]

	Result [mg/kg]				
Analyte	Sample	Sample	Sample		
	017+024+027	018	019		
Lead	N.D.	31.6	27.3		
Limit		<90			
Conclusion	Pass	Pass	Pass		

/	/	Result [mg/kg]				
Analyte	Sample	Sample	Sample			
	020	021	022			
Lead	12.7	38.2	29.4			
Limit		<90				
Conclusion	Pass	Pass	Pass			

		Result [mg/kg]	
Analyte	Sample 025	Sample 026	Sample 028
Lead	N.D.	N.D.	N.D.
Limit		<90	
Conclusion	Pass	Pass	Pass

	Result [mg/kg]				
Analyte	Sample	Sample	Sample		
	029 030 031				
Lead	N.D.	N.D.	N.D.		
Limit	<90				
Conclusion	Pass	Pass	Pass		

		Result [mg/kg] Sample Sample Sample 032 033 034				
Analyte	-					
Lead	14.8	13.0	N.D.			
Limit		<90				
Conclusion	Pass	Pass	Pass			

Note 1. "mg/kg" denotes milligram per kilogram

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Laboratory: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch Building 12&13, Zhiheng Wisdomland Business Park,

Nantou Checkpoint Road 2, 518052, P. R. China

Page 15 of 25



Dated: 2019-11-25



3.5 Total Lead Content Test

Consumer Products Containing Lead Regulations SOR/2018-83
Acid digestion / Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

[Reporting Limit: 10.0mg/kg]

	Result [mg/kg]				
Analyte	Sample	Sample	Sample		
	035	036	037		
Lead	36.3	N.D.	N.D.		
Limit		<90			
Conclusion	Pass	Pass	Pass		

	Resu	lt [mg/kg]				
Analyte	Sample	Sample				
	038	039				
Lead	N.D.	N.D.				
Limit		<90				
Conclusion	Pass	Pass				

Note 1. "mg/kg" denotes milligram per kilogram

- 2. "<" denotes less than
- 3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.6 Total Lead Content Test

Surface Coating Materials Regulations SOR/2016-193

Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	Result	[mg/kg]			
Analyte	Sample	Sample			
-	002	014			
Lead	N.D.	N.D.			
Limit	<	<90			
Conclusion	Pass	Pass			

Note 1. "mg/kg" denotes milligram per kilogram

- 2. "<" denotes less than
- 3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

Dated: 2019-11-25



Phthalates Content (11P) 3.7

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

		F	Results [%	Client's	
Test Items	CAS No.	Sample 001+040 +041	Sample 002	Sample 003	Specification [%]
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-n-pentyphthalat (DNPP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion	1	Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

Phone: +86 755 8828 6998 Fax: +86 755 8828 5299 E-mail: toys_hardline@tuv-sud.hk Web: http://www.tuv-sud.cn

Dated: 2019-11-25



Phthalates Content (11P) 3.7

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

		F	Results [%	Client's	
Test Items	CAS No.	Sample 014	Sample 017+024 +027	Sample 031	Specification [%]
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Diethyl phthalate (DEP)	84-66-2	N.D.	N.D.	N.D.	<0.1
Butylbenzylphthalat (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-n-pentyphthalat (DNPP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

Phone: +86 755 8828 6998 Fax: +86 755 8828 5299 E-mail: toys_hardline@tuv-sud.hk Web: http://www.tuv-sud.cn

Dated: 2019-11-25



Phthalates Content (11P) 3.7

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

		Results [%]	Client's Specification	
Test Items	CAS No.	Sample		
		039	[%]	
Di-(2-ethylhexyl)-phthalat (DEHP)	117-81-7	N.D.	<0.1	
Dibutylbenzylphthalat (DBP)	84-74-2	N.D.	<0.1	
Diethyl phthalate (DEP)	84-66-2	N.D.	<0.1	
Butylbenzylphthalat (BBP)	85-68-7	N.D.	<0.1	
Di-iso-butylphthalat (DIBP)	84-69-5	N.D.	<0.1	
Di-isononyl phthalate (DINP)	28553-12-0 , 68515-48-0	N.D.	<0.1	
Di-isodecylphthalat (DIDP)	26761-40-0 , 68515-49-1	N.D.	<0.1	
Di-n-octylphthalat (DNOP)	117-84-0	N.D.	<0.1	
Di-n-hexyl phthalate (DnHP)	84-75-3	N.D.	<0.1	
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	<0.1	
Di-n-pentyphthalat (DNPP)	131-18-0	N.D.	<0.1	
Conclusion	<u> </u>	Pass		

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

Phone: +86 755 8828 6998 Fax: +86 755 8828 5299 E-mail: toys_hardline@tuv-sud.hk Web: http://www.tuv-sud.cn

Dated: 2019-11-25



3.8 US California Proposition 65 - Phthalates Content (6P)

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

		Results [%]			Client's
Test Items	CAS No.	Sample 001+040 +041	Sample 002	Sample 003	Specification [%]
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Conclusion	GIII	Pass	Pass	Pass	-

		Results [%]			Client's
Test Items	CAS No.	Sample 014	Sample 017+024 +027	Sample 031	Specification [%]
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

Dated: 2019-11-25



3.8 US California Proposition 65 - Phthalates Content (6P)

Test method: In-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS). [Reporting limit: 0.005%]

Test Items	CAS No.	Results [%] Sample 039	Client's Specification [%]
Dibutyl phthalate, (DBP)	84-74-2	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	<0.1
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	N.D.	<0.1
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	<0.1
Conclusion		Pass	-

Note 1. "%" denotes percentage by weight

2. "<" denotes less than

3. "N.D." denotes Not Detected with Detection Limit 0.005%

Dated: 2019-11-25



3.9 U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P) CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates [Reporting Limit = 0.005%]

	CAS No.	Results [%]			
Phthalates		Sample 001+040 +041	Sample 002	Sample 003	Limit [%]
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

^{2. &}quot;<" denotes less than

^{3. &}quot;N.D." denotes Not Detected with Detection Limit 0.005%

Dated: 2019-11-25



U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P) 3.9 CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates [Reporting Limit = 0.005%]

	CAS No.	Results [%]			
Phthalates		Sample 014	Sample 017+024 +027	Sample 031	Limit [%]
Dibutyl phthalate, (DBP)	84-74-2	N.D.	N.D.	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	N.D.	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	N.D.	N.D.	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	N.D.	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	N.D.	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	N.D.	N.D.	<0.1
Conclusion		Pass	Pass	Pass	-

Note 1. "%" denotes percentage by weight

Phone: +86 755 8828 6998 Fax: +86 755 8828 5299 E-mail: toys_hardline@tuv-sud.hk Web: http://www.tuv-sud.cn

^{2. &}quot;<" denotes less than

^{3. &}quot;N.D." denotes Not Detected with Detection Limit 0.005%

Dated: 2019-11-25



3.9 U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P) CPSC-CH-C1001-09.4 – Standard Operating Procedure for Determination of Phthalates [Reporting Limit = 0.005%]

		Results [%]	l imais
Phthalates	CAS No.	Sample 039	Limit [%]
Dibutyl phthalate, (DBP)	84-74-2	N.D.	<0.1
Benzyl butyl phthalate, (BBP)	85-68-7	N.D.	<0.1
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	N.D.	<0.1
Diisobutylphthalate, (DIBP)	84-69-5	N.D.	<0.1
Di-n-hexyl phthalate (DHEXP)	84-75-3	N.D.	<0.1
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	<0.1
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	N.D.	<0.1
Di-n-pentyl phthalates (DPENP)	131-18-0	N.D.	<0.1
Conclusion		Pass	-

Note 1. "%" denotes percentage by weight

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

^{2. &}quot;<" denotes less than

^{3. &}quot;N.D." denotes Not Detected with Detection Limit 0.005%

Dated: 2019-11-25



3.10 Tungsten Content Test

Test method: EPA 3050B:1996, analyzed by Inductively Coupled Plasma Optical Emission

Spectrometer (ICP-OES). [Reporting Limit: 10.0mg/kg]

	Results [mg/kg]	Client's
Test Item	Sample 036	Specification [mg/kg]
Tungsten	N.D.	-
Conclusion	Report as is	-

Note:

- "mg/kg" denotes milligram per kilogram
- "<" denotes less than
- "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

3.11 Total Mercury Content Test

Surface Coating Materials Regulations SOR/2016-193
Microwave Digestion, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10mg/kg]

	Results	Limit	
Test Item	Sample 002	Sample 014	[mg/kg]
Mercury	N.D.	N.D.	<10
Conclusion	Pass	Pass	-

OFFID

Note 1. "mg/kg" denotes milligram per kilogram

- 2. "<" denotes less than
- 3. "N.D." denotes Not Detected with Detection Limit 10.0mg/kg

-- END OF TEST REPORT--

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: toys_hardline@tuv-sud.hk
Web: http://www.tuv-sud.cn

Regd. Office:

Nantou Checkpoint Road 2, 518052, P. R. China