

Test Report # 18W-013750 Date of Report Issue: December 10, 2018

Date of Sample Received: December 3, 2018 Pages: Page 1 of 18

CLIENT INFORMATION:

Company: Spector & Co.

Address: -

SAMPLE INFORMATION:

Description: Nomad Must Haves Collection

Assortment: BG106

Model/style No.: BG106, BG104, BG204, BG400

SKU No.: PO#69689 BATCH 201708

PO No.: PO#69689
Factory/Supplier: USB059
Quantity Submitted: 1 PCS

Country of Distribution: Canada, United States

Country of Origin: China

Testing Period: 12/06/2018-12/10/2018

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

kein.lee

Kevin Lee

Technical Manager



Test Report # 18W-013750 Date of Report Issue: December 10, 2018

Date of Sample Received: December 3, 2018 Pages: Page 2 of 18

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Paints and Surface Coatings
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	California Proposition 65, Total Cadmium in Paints and Surface Coatings
PASS	California Proposition 65, Total Cadmium in Substrate Materials
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates(DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)
PASS	Client's Requirement, Phthalates content



Test Report # 18W-013750 Pages: Page 3 of 18

DETAILED RESULTS:

California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1					Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	28					90
Conclusion	PASS					

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Specimen No	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
1	18W-013740	1	December 10, 2018



Test Report # 18W-013750 Pages: Page 4 of 18

DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2	3	4+14	5	6	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	36	18	ND	29	19	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	7	8	9	10	11	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	24	27	21	ND	23	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	12+13+15	16	17	18+19		Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND		100
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Chasiman Na	Transferre	Data of Issue		
Specimen No.	Report No.	Specimen No.	Date of Issue	
2	18W-013740	2	December 10, 2018	
3	18W-013740	3	December 10, 2018	

+ Tel: (8 + 5/F A2 Building + No. 1213 Huoju South Road + Puyan Street + Binjiang District + Hangzhou + C



Test Report # 18W-013750 Pages: Page 5 of 18

DETAILED RESULTS:

Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1					Total
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	28					90
Conclusion	PASS					

Note:

mg/kg=Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit: Pb=15 mg/kg;)

Data Consolidation Reference:

Cnaciman Na	Transferre	Data of Issue	
Specimen No.	Report No. Specimen No.		Date of Issue
1	18W-013740	1	December 10, 2018

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD • Email: Labtesting@asiainspection.com • Tel: (8 • 5/F A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • C



Test Report # 18W-013750 Pages: Page 6 of 18

DETAILED RESULTS:

Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2	3	4+14	5	6	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	36	18	ND	29	19	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	7	8	9	10	11	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	24	27	21	ND	23	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	12+13+15	16	17	18+19		Limit
Tost Itom	Result	Result	Result	Result	Result	(mg/kg)
Test Item	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(1116/116/
Total Lead (Pb)	ND	ND	ND	ND		90
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg=Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Data Consolidation Reference:

Spacimon No	Transferre	Date of Issue	
Specifier No.	Specimen No. Report No.		Date of issue
2	18W-013740	2	December 10, 2018
3	18W-013740	3	December 10, 2018



Test Report # 18W-013750 Pages: Page 7 of 18

DETAILED RESULTS:

California Proposition 65, Total Cadmium in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1					Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND					75
Conclusion	PASS					

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

	. — .			
Cnasimon Na	Transferre	Data of Issue		
Specimen No.	Report No.	Specimen No.	Date of Issue	
1	18W-013740	1	December 10, 2018	



Test Report # 18W-013750 Pages: Page 8 of 18

DETAILED RESULTS:

California Proposition 65, Total Cadmium in Substrate Materials

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2	3	4+14	5	6	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	7	8	9	10	11	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	12+13+15	16	17	18+19		Limit
Test Item	Result	Result	Result	Result	Result	(mg/kg)
lest item	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(0, 0,
Total Cadmium (Cd)	ND	ND	ND	ND		75
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Creation on No	Transferre	Date of Issue	
Specimen No. Report No.			
2	18W-013740	2	December 10, 2018
3	18W-013740	3	December 10, 2018



Test Report # 18W-013750 Pages: Page 9 of 18

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	0.	1	4+14	12+13+15	16	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Specimen No	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
1	18W-013740	1	December 10, 2018



Test Report # 18W-013750 Pages: Page 10 of 18

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	Specimen No.		18+19			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND			1000
Conclusion	1	PASS	PASS			

Note.

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

* Email: Labtesting@asiainspection.com

* Tel: (8

* 5/F A2 Building

* No. 1213 Huoju South Road

* Puyan Street

* Binjiang District

* Hangzhou

* Conclusion(s) in this report relate to the sample(s) tested as described herein.



Test Report # 18W-013750 Pages: Page 11 of 18

DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4(Modified), In-House Method Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	0.	1	4+14	12+13+15	16	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Data Consolidation Reference:

Spacimon No	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
1	18W-013740	1	December 10, 2018



Test Report # 18W-013750 Pages: Page 12 of 18

DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4(Modified), In-House Method Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		17	18+19			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND			1000
Conclusion		PASS	PASS			

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



Test Report # 18W-013750 Pages: Page 13 of 18

DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	4+14	12+13+15	16	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	ND	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD • Email: Labtesting@asiainspection.com • Tel: (8 • 5/F A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • C



Test Report # 18W-013750 Pages: Page 14 of 18

Data Consolidation Reference:

Spacimon No	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
1	18W-013740	1	December 10, 2018



Test Report # 18W-013750 Pages: Page 15 of 18

DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		17	18+19			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND			1000
Diethyl phthalate (DEP)	84-66-2	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND			1000
Conclusion		PASS	PASS			

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



Test Report # 18W-013750 Pages: Page 16 of 18

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Black coating	Inside zipper head
2	Silvery metal	Inside zipper puller
3	Silvery metal	Inside zipper slider
4	Black plastic	Inside zipper teeth
5	Bright silvery metal	Main zipper puller
6	Bright silvery metal	Main zipper slider
7	Bright silvery metal	Main zipper teeth
8	Bright silvery metal	Hook main body
9	Bright silvery metal	Hook clasp push rod
10	Bright silvery metal	Hook shaft
11	Bright silvery metal	Hook base
12	Deep grey soft plastic	Inside elastic
13	Grey foam	Inner filler
14	Black plastic	Adjustable buckle
15	White foam	Inner filler
16	Black printed white textile	Label
17	Black coated grey textile	Main body
18	Black plastic	Hook main body
19	Black plastic	Hook base



Test Report # 18W-013750 Pages: Page 17 of 18

SAMPLE PHOTO:







Test Report # 18W-013750 Pages: Page 18 of 18

SAMPLE PHOTO:



-End Report-